

# Gekatex Novapro

## Fabric Technical Data – Novapro

Preliminary Data\*

Property		Value	Unit	Test method
Composition	Polyester	30	%	
	Rayon	70	%	
Basis weight		80 +/- 10%	g/m <sup>2</sup>	ASTM D3776 CNS-1479
Thickness		0.75 +/-0.03	mm	ERT 30.5-99 CNS-1479
Grab tensile breaking strength (dry)	MD	6.23	N (kg)	ASTM D5034 CNS-9520
	XD	1.04	N (kg)	
Dimensions	cloth	60x40 cm	U folded	10x50/case
Binder content Anti Bactericide agent		10% Yes	Type acrylic	

\* data based on limited testing. For guidance only.  
MD- LENGTHWISE, XD- CROSSWISE